Chicora Foundation Mortar Analysis Data Sheet

Name:	Pon Pon 14	Sample No.:	2005-3
Date:	1/24/05	Origin of Sample:	Interior wall stucco from wall

Visual Description of sample (color, texture, hardness, inclusions, etc.): Hard, slightly friable, white inclusions from 2mm to < 1mm. Color is pale brown 10 YR 6/3

Mortar Analysis

Original weight of powdered sample	19.49
Weight of filter paper	0.84
Weight of filter paper + dry fines	1.90
Weight dry fines	1.06
Weight of dry sand	8.49
% of sand	43.56
% of fines	5.44
% of disolved binder	51.00

Observations (dissolution of binder, color of liquid, reaction): Moderately vigorous, short-lived, dark brown liquid.

Characterization of Sand:

				wt (gm)	%
Microscopic Examination:		wt./% finer than	4.75mm	0.00	0
2.36mm to 1.18mm angular pieces of conglom	erate material.		2.36mm	0.11	1.295642
710µm a few flecks of angular white material,	very few subangular		1.18mm	0.30	3.533569
pieces of quartz.	300µm to 53µm		600µm	0.42	4.946996
very few small black flecks of UID material.			300µm	0.83	9.776207
			150µm	2.08	24.49941
			75µm	4.21	49.58775
			53µm	0.54	6.360424
			38µm	0.00	0
		Total sand weight		8.49	

Total sand weight

Munsell Color(s) of Sand:

light grayish brown 10 YR 6/2

